

# Color K-88 Admix

**100% acrylic admixture  
for cementitious materials,  
formulated  
to provide color.**

**WHERE TO USE  
White Conpro Stucco,  
to obtain Masonry Series Colors,  
refer to Conproco Product & Color  
Selection Guide\*.**

## PERFORMANCE CHARACTERISTICS

### Colorfast

- Provides excellent dispersion of color through mix.

### Color choices

- Choose from 14 natural earth tone colors.

### Promotes curing

- Reduces need to moist cure materials in most cases. Reduces shrinkage induced cracking.

### Increases bond

- Promotes chemical adhesion to substrate.

### Durability

- Increases compressive and tensile strengths. Increases freeze/thaw resistance.

### Water resistance

- Increases density and improves resistance to water entry.

\**Color K-88 Admix* can be used with Conproco products *Structural Skin*, *Plastermix*, and *Conpro Seal*, to achieve colors similar, but not identical to *Conpro Stucco*.

## SURFACE PREPARATION

- *Color K-88 Admix* is an admixture. Refer to the specific product bulletin for material to used for surface preparation.

## PRIMING

- Follow the instructions of the material to which *Color K-88 Admix* will be added.

## MIXING

- Stir or vigorously shake container and pour complete contents into mix. Ensure that all of the liquid and pigment are emptied from container.

## CURING

- Follow the instructions of the Conproco product to which *Color K-88 Admix* is added.

## CLEAN UP

- Clean tools and equipment with water.

# Color K-88 Admix

## COVERAGE/YIELD

- 1 quart per 50 lbs. bag of *Conpro Stucco*.

## PRODUCT HANDLING

### Packaging

- Quart containers.

### Shelf Life

- 18 months in unopened containers.

### Storage

- Protect from freezing.
- Transport and store in cool, clean, dry conditions in unopened containers.
- High temperature will reduce shelf life.

## LIMITATIONS

- Do not apply if temperature of substrate is below 45°F.
- Do not apply if ambient temperature is below 45°F.
- Do not re-temper mixes modified with *Color K-88 Admix*.

## HEALTH AND SAFETY

- Do not ingest.
- Avoid contact with skin and eyes.
- Avoid breathing vapors.
- Refer to Material Safety Data Sheet (MSDS) for additional information.

## FIRST AID

- In case of skin contact, wash thoroughly with soap and water. For eye contact, flush immediately with a high volume of water for at least 15 minutes and contact a medical professional. For respiratory problems, remove person to fresh air. If respiratory difficulty persists, contact a medical professional.

## DISPOSAL

- Dispose of material in accordance with local, state or federal regulations.

## TECHNICAL DATA

Physical state and appearance		Colored liquid
Base		Aqueous
Polymer		100% acrylic
Odor		Ammoniacal
pH		>9.5
Percent solids by weight	Wet mix	45 - 65% by weight dependent on color
Density of liquid coatings	ASTM D1475	8.4 lbs./gal.
		<b>7 Days</b> <b>14 Days</b> <b>28 Days</b>
Compressive strength	ASTM C109	
Design mix without Color K-88 Admix – psi		2725    3375    3725
Design mix with Color K-88 Admix – psi		3400    4150    4700
Percent increase – %		25    23    26
Tensile strength	ASTM C307	
Design mix without Color K-88 Admix – psi		95    360    360
Design mix with Color K-88 Admix – psi		385    390    400
Percent increase – %		30    8    11

### FOR PROFESSIONAL USE ONLY

Conproco Corp. warrants this product for one year from date of installation to be free from manufacturing defects and to meet the technical properties on the current technical data sheet if used as directed within shelf life. User determines suitability of product for use and assumes all risks. Buyer's sole remedy shall be limited to the purchase price or replacement of product exclusive of labor or cost of labor. October 2010.

NO OTHER WARRANTIES EXPRESS OR IMPLIED SHALL APPLY INCLUDING ANY WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE. CONPROCO CORP. SHALL NOT BE LIABLE UNDER ANY LEGAL THEORY FOR SPECIAL OR CONSEQUENTIAL DAMAGES.

**conproco**<sup>®</sup>  
CORPORATION

17 PRODUCTION DRIVE, DOVER, NEW HAMPSHIRE 03820  
TELEPHONE 800.258.3500 • FAX 603.743.5744 • WEB ADDRESS [www.conproco.com](http://www.conproco.com)