

# Elastideck

**Spray, roller or squeegee applied, acrylic modified, cementitious, flexible, waterproof membrane. Available in 14 standard colors.**

**WHERE TO USE**  
**Decorative coating for balconies, walkways, driveways, planters and parapets.**

## PERFORMANCE CHARACTERISTICS

### Flexible

- Able to bridge minor cracking.

### Waterproof

- Positive side waterproofing membrane requires two coats.

### Decorative

- Available in 14 colors to complement surroundings.

### Durable

- Resistant to weathering action, excellent freeze/thaw stability and abrasion resistance.

### Very low permeability

- Resistant to deicing salts, chloride, and chemical attack, and environmental pollution.

### Breathability

- Will not cause damage to structure by restricting moisture vapor flow. Ideal for slab-on-grade.

### Two component

- Pre-measured, pigmented liquid with powder in one container for consistent performance.

## SURFACE PREPARATION

- Remove loose and deteriorated material, laitance, dirt, dust, oil and any surface contaminants that will inhibit proper bond.
- Remove a minimum 1/16 inch of surface (CSP 5) by abrasive blasting, steel shotblasting, scarifying, needle-scaling or high pressure water.
- Avoid bruising or micro cracking during surface preparation. Refer to ICRI Surface Preparation Guide 03732.
- Apply *Conpro Start* where a consolidant is of benefit.
- Saturate substrate with clean water, (saturated surface dry/SSD), with no standing water during *Priming or Application*.

## PRIMING

- No priming is required under normal circumstances.

## MIXING

- Mechanically mix using a low speed drill (400 - 600 rpm) and mixing paddle or mortar mixer.
- Thoroughly shake *Elastideck* admix to disperse the pigment.
- Pour *Elastideck* admix into a clean mixing vessel and slowly add all of the powder.
- Mix continuously for 3 minutes to a uniform, lump-free consistency.
- Do not over mix, as this will entrain excess air.
- Do not re-temper.

## APPLICATION

- At the time of application, surfaces should be saturated surface dry (SSD) but hold no standing water.
- Clean and pre-stripe non-structural cracks (up to 1/16 inch) with one 4 inch wide, 50 mils. application of material.
- Dynamic cracks, joints and transitions (wall-to-slab) must be properly detailed with a closed cell backer rod and polyurethane sealant. Refer to SWRI Sealants, The Professionals' Guide.
- Apply 4 - 6 inch wide stripe of material over cured sealant. Embed mesh fabric while material is plastic.
- Apply a 50 mils. coat over the entire surface with a stiff bristle brush, heavy nap roller, sponge float, squeegee or spray.
- Work material into substrate to promote proper adhesion.
- Do not exceed 60 mils. per coat.
- Apply a second 50 mils. coat for waterproofing and longer service life.
- Do not overwork the finish.
- *Elastideck* must cure to a point that it will accept light foot traffic prior to application of *Super Color Stain HR* (approximately 24 hours @ 70°F and 50%RH).
- Apply *Super Color Stain HR* in the same color as *Elastideck* to provide added protection, color uniformity and stain resistance.

## CURING

- Protect repair from direct sunlight, wind, rain and frost during curing period.

## CLEAN UP

- Clean tools and equipment with water immediately after use. Cured material must be removed mechanically.

# Elastideck

## COVERAGE/YIELD

- 160 ft.<sup>2</sup>/50 lbs. kit per coat @ 50 mils.

## PRODUCT HANDLING

### Packaging

- 50 lbs. plastic pail contains 25 lbs. of powder and 2-1/2 gallons of admix.

### Shelf Life

- 18 months when properly stored.

### Storage

- Transport and store in cool, clean, dry conditions in unopened containers.
- High temperature or high humidity will reduce shelf life.
- Protect from freezing.

## LIMITATIONS

- Do not apply unless substrate and ambient temperature can be maintained at a minimum of 45°F for 24 hours. Refer to ACI Cold Weather Application Guidelines.
- Protect application from precipitation and high wind for at least 8 hours.
- Do not place rubber mats or equivalent on *Elastideck* for 14 days.
- Do not add water.
- Do not re-temper, polymer modified materials.
- Avoid overworking material during placement.

## HEALTH AND SAFETY

- Product is alkaline.
- Do not ingest.
- Avoid breathing dust.
- Avoid contact with skin and eyes.
- Refer to Material Safety Data Sheet (MSDS) for additional information.

## FIRST AID

- In case of skin contact, wash thoroughly with soap and water. For eye contact, flush immediately with a high volume of water for at least 15 minutes and contact a medical professional. For respiratory problems, remove person to fresh air.

## DISPOSAL

- Dispose of material in accordance with local, state or federal regulations.

## TECHNICAL DATA

Physical state and appearance		White powder and admix
Base		
Powder		Portland cement
Liquid		Milky, liquid emulsion
Polymer		Styrene acrylic
pH	Wet mix	>12
VOC	ASTM D3960	Less than 0.15 lbs./gal. (per mixed kit)
Setting time	ASTM C953	Initial 120 minutes – Final 300 minutes
Elongation	ASTM D2370	180%
Water vapor transmission	ASTM E96	8 - 10 perms
Resistance to hydrostatic pressure	CRD-48-73	100% reduction
Accelerated weathering	ASTM C1519	2000 hours – no effect
Taber abrasion resistance	ASTM C1353	2000 cycles, less than 0.8% weight loss (H22 wheel with 500 grams of weight)
Tensile strength – psi	ASTM C307	810
Mandrel bend test	ASTM D522	1/8 in. @ 68°F and 27°F

### FOR PROFESSIONAL USE ONLY

Conproco Corp. warrants this product for one year from date of installation to be free from manufacturing defects and to meet the technical properties on the current technical data sheet if used as directed within shelf life. User determines suitability of product for use and assumes all risks. Buyer's sole remedy shall be limited to the purchase price or replacement of product exclusive of labor or cost of labor. October 2010.

NO OTHER WARRANTIES EXPRESS OR IMPLIED SHALL APPLY INCLUDING ANY WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE. CONPROCO CORP. SHALL NOT BE LIABLE UNDER ANY LEGAL THEORY FOR SPECIAL OR CONSEQUENTIAL DAMAGES.

**conproco**<sup>®</sup>  
CORPORATION

17 PRODUCTION DRIVE, DOVER, NEW HAMPSHIRE 03820  
TELEPHONE 800.258.3500 • FAX 603.743.5744 • WEB ADDRESS [www.conproco.com](http://www.conproco.com)