

M3P

**Spray, roller
or brush applied,
mineral silicate
paint.**

WHERE TO USE
**Long term protection and
enhanced aesthetics of concrete,
masonry and stone. Used when objective
is to change color of substrate.**

PERFORMANCE CHARACTERISTICS*

Anti-carbonation

- Reacts with calcium hydroxide at surface, mitigating carbonation to depth of penetration.

Water repellent

- Siloxane component provides long term protection from water and water borne contaminants.

Non-film forming

- Will not peel, blister or flake.

Breathability

- 97% vapor permeable.

Stable

- Unaffected by UV.
Fire resistant.

Colorfast

- Unique iron oxide pigment system resists fading.

Environmentally friendly

- Water based, low odor, low VOC.

Ease of application

- Single component, stir and apply.

Extensive color spectrum

- 57 standard colors, plus *Matrix* colors and custom matching.

**Primex* is a non-pigmented version of *M3P*. The physical and performance characteristics are identical with the exception of color.

SURFACE PREPARATION

- Remove loose and deteriorated material, laitance, dirt, dust, oil and any surface contaminants that will inhibit proper penetration.
- Prepare surface to be sandpaper-like texture (CSP 3) by mechanical abrasion or water blasting. Refer to ICRI Surface Preparation Guide 03732 for information about Concrete Surface Profile (CSP).
- Surface must be dry and frost free.
- New concrete must cure at least 14 days before application.

PRIMING

- Apply a uniform application of *Primex*.
- For best results spray apply beginning at the bottom of the structure and work to the top.
- Allow to react for 12 hours before applying *M3P*.

MIXING

- Stir or mechanically mix using a low speed drill (400 - 600) until homogenous.
- Mix pails from different batches when an entire surface is visible.

APPLICATION

- Apply a test sample to determine suitability. Ensure by visual inspection that *Primex* and *M3P* have penetrated the substrate. A white film on the surface after either material reacts – 12 hours indicates substrate is either too dense for proper penetration or a previous treatment such as a water repellent has been applied.
- Substrate temperature must be above 45°F.
- Ambient temperature must be above 45°F for the entire curing period.
- For roller applications use a 3/8 - 1/2 inch synthetic nap roller depending on texture of substrate.
- For spray applications use an airless sprayer with a 0.017 - 0.021 tip. Refer to *Conproco Black Book*.
- Work to pre-determined break points in the structure.
- Maintain a wet edge.
- Allow *Primex* to react for 12 hours before applying *M3P*.
- If *Primex* has been applied, a second application of *M3P* can be applied after the first is dry-to-touch.

CURING

- Protect from moisture for 24 hours.

CLEAN UP

- Clean tools and equipment with water. Clean adjacent areas with water before material dries.

M3P

COVERAGE/YIELD

- *M3P* – 170 - 300 ft.²/gal.
- *Primex* – 120 - 200 ft.²/gal.

PRODUCT HANDLING

Packaging

- 1 and 5 gallon containers.

Shelf Life

- 18 months in unopened containers.

Storage

- Protect from freezing.
- Transport and store in cool, clean, dry conditions in unopened containers.
- High temperature will reduce shelf life.

LIMITATIONS

- Do not apply if precipitation is forecast within 24 hours of application.
- Do not apply in strong winds.
- Do not apply to frozen surfaces.
- Do not apply if temperature of substrate is below 45°F.
- Do not apply if ambient temperature is below 45°F.

HEALTH AND SAFETY

- Product is alkaline.
- Do not ingest.
- Avoid contact with skin and eyes.
- Refer to Material Safety Data Sheet (MSDS) for additional information.

FIRST AID

- In case of skin contact, wash thoroughly with soap and water. For eye contact, flush immediately with a high volume of water for at least 15 minutes and contact a medical professional. For respiratory problems, remove person to fresh air. If respiratory difficulty persists, contact a medical professional.

DISPOSAL

- Dispose of material in accordance with local, state or federal regulations.

TECHNICAL DATA

Physical state and appearance		Thick liquid emulsion – natural
Base		Aqueous
pH		11.2
Percent solids by weight		51%
Viscosity	ASTM D562	95 - 105 KU – paint paddle
Density of liquid coatings	ASTM D1475	9.4 lbs./gal.
Drying time		1 hour @ 65°F – dry to touch
Fungus resistance	Fed. Spec. TT-P-19D	No growth
Accelerated weathering – QUV	ASTM G154	2000 hours – UV-B cycled with condensation – no effect
Hiding power of coating @ 5 mils.	ASTM D2805	Excellent
Water penetration and leakage	ASTM E514	100% reduction
Heat stability	ASTM C932	Pass – 2 weeks @ 120°F
Mud cracking @ 10 mils.		None
Primex		
Physical state and appearance		White – milky liquid
Base		Aqueous
pH		11.2
Percent solids by weight		9.7%
Viscosity	ASTM D562	26 KU – paint paddle
Density of liquid coatings	ASTM D1475	9.1 lbs./gal.

FOR PROFESSIONAL USE ONLY

Conproco Corp. warrants this product for one year from date of installation to be free from manufacturing defects and to meet the technical properties on the current technical data sheet if used as directed within shelf life. User determines suitability of product for use and assumes all risks. Buyer's sole remedy shall be limited to the purchase price or replacement of product exclusive of labor or cost of labor. January 2005.

NO OTHER WARRANTIES EXPRESS OR IMPLIED SHALL APPLY INCLUDING ANY WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE. CONPROCO CORP. SHALL NOT BE LIABLE UNDER ANY LEGAL THEORY FOR SPECIAL OR CONSEQUENTIAL DAMAGES.

conproco[®]
CORPORATION

17 PRODUCTION DRIVE, DOVER, NEW HAMPSHIRE 03820
TELEPHONE 800.258.3500 • FAX 603.743.5744 • WEB ADDRESS www.conproco.com