

One Shot Ag

**Trowel applied,
single component,
polymer modified,
Portland cement concrete
with ECB-Tech corrosion protection.**

WHERE TO USE
Horizontal concrete
such as balconies, industrial floors,
parking surfaces and stairs
from 1/2 - 6 inches.

PERFORMANCE CHARACTERISTICS

Low shrinkage

- Maintains integrity of repair, resists cracking.

Thermal compatibility

- Prevents delamination due to temperature change.

Corrosion protection

- Protects reinforcing steel in repair zone and suppresses ring anode effect.

Durable

- Resistant to weathering action, excellent freeze/thaw stability and abrasion resistance.

Very low permeability

- Resistant to deicing salts, carbonation, chloride, and chemical attack.

Dimensionally stable

- Ideal for large areas.

Abrasion resistant

- Hard, durable surface for long term wear.

Single component

- Polymer and aggregate included – ready to use.

SURFACE PREPARATION

- Remove loose and deteriorated material, laitance, dirt, dust, oil and any surface contaminants that will inhibit proper bond.
- Saw cut edges with a diamond blade at a 90° angle to eliminate feather edging. Avoid polishing the edges, as this will inhibit bond.
- Avoid bruising or micro cracking during surface preparation. Refer to ICRI Surface Preparation Guide 03732.
- Repair zone must be a minimum of 1/2 inch deep, of simple geometry, with no complex edge conditions.
- Avoid long narrow repairs; these have a greater tendency to crack.

- Apply *Conpro Start* where a consolidant is of benefit.
- Saturate substrate with clean water, (saturated surface dry/SSD), with no standing water during *Priming* or *Application*.
- Remove concrete from corroded steel and several inches beyond to expose non-corroded steel.
- Provide a 3/4 inch clearance between the concrete and steel.
- Damaged reinforcing steel should be inspected by a qualified engineer and appropriate action taken.

PRIMING

Concrete

- Apply *Conpro Primer* as a bonding primer to all exposed surfaces. Refer to the individual product technical data bulletin for information.

Reinforcing Steel

- Remove all scaling rust from reinforcing steel.
- Apply *ECB* anti-corrosion coating.

MIXING

- Mechanically mix using a low speed drill (400 - 600 rpm) and mixing paddle or mortar mixer.
- Pour 3 quarts of potable water into a clean mixing vessel and slowly add all of the powder.
- Mix continuously for 3 minutes to a uniform, lump-free consistency.
- Add up to 1 pint of additional water if needed.
- Allow to "breathe" for 1 minute and remix for 1 minute. This will improve workability and open time.
- Do not over mix, as this will entrain excess air.

APPLICATION

- At the time of application, surfaces should be saturated surface dry (SSD) but hold no standing water.
- Follow instructions for *Priming*.
- Form applications must be consolidated with vibrator.
- Place material continuously to break points.
- Finish with a magnesium float or trowel.
- Avoid overworking material during placement and finishing – this will produce surface (map) cracking.

CURING

- Dampen the repair with a fine mist of water for 24 hours or moist cure with wet burlap and polyethylene. Alternatively, apply *Conpro C309 Cure & Seal*.
- Protect repair from direct sunlight, wind, rain and frost during curing period.

CLEAN UP

- Clean tools and equipment with water immediately after use. Cured material must be removed mechanically.

One Shot Ag

COVERAGE/YIELD

- 0.65 ft.³/80 lbs. – 15 ft.² @ 1/2 inch.

PRODUCT HANDLING

Packaging

- 80 lbs. multi-wall, poly lined bags.

Shelf Life

- 12 months when properly stored.

Storage

- Transport and store in cool, clean, dry conditions in unopened containers.
- High temperature or high humidity will reduce shelf life.

LIMITATIONS

- Do not apply unless substrate and ambient temperature can be maintained at a minimum of 40°F for 24 hours. Refer to ACI Cold Weather Application Guidelines.
- Cold mixing water and low temperature will retard set. Hot water and high temperature will accelerate set.
- Protect application from precipitation and high wind for at least 8 hours.
- Do not re-temper, this will damage the cross-linking of the polymer and cause cracking and loss of bond.
- Do not add more water than specified – this will lower strengths and cause shrinkage cracking.
- Avoid overworking material during placement and finishing – this will produce surface (map) cracking.

HEALTH AND SAFETY

- Product is alkaline.
- Do not ingest.
- Avoid breathing dust.
- Avoid contact with skin and eyes.
- Refer to Material Safety Data Sheet (MSDS) for additional information.

FIRST AID

- In case of skin contact, wash thoroughly with soap and water. For eye contact, flush immediately with a high volume of water for at least 15 minutes and contact a medical professional. For respiratory problems, remove person to fresh air.

DISPOSAL

- Dispose of material in accordance with local, state or federal regulations.

TECHNICAL DATA

Physical state and appearance		Dry powder with aggregate	
Base		Portland cement	
pH	Wet mix	>12	
Aggregate type		Sharp quartz silica with 3/8 inch pea stone	
Water/cement ratio		0.49*	
Density	Wet mix	140 lbs./ft. ³	
Setting time by vicat needle	ASTM C191	Initial 45 minutes – Final 180 minutes	
Slump	ASTM C143	2 - 3 inches @ 3 quarts – water/bag 4 - 5 inches @ 3.5 quarts – water/bag	
Percent air by volumetric	ASTM C173	6%	
Resistance to deicing chemicals under freeze/thaw	ASTM C672	50 cycles – 0 rating – no effect	
Length change	ASTM C157	<500 µstrains @ 28 days	
Modulus of elasticity	ASTM C469	2.8 x 10 ⁶	
Slant shear bond strength – epoxy	ASTM C882	1700 psi without slurry coat 1775 psi with slurry coat	
		7 Days 14 Days 28 Days	
Compressive strength – psi	ASTM C109	5650 5800 6525	
Splitting tensile strength – cylinders – psi	ASTM C496		585

*Tests run using 3 quarts water per 80 lbs. bag of One Shot Ag.

FOR PROFESSIONAL USE ONLY

Conproco Corp. warrants this product for one year from date of installation to be free from manufacturing defects and to meet the technical properties on the current technical data sheet if used as directed within shelf life. User determines suitability of product for use and assumes all risks. Buyer's sole remedy shall be limited to the purchase price or replacement of product exclusive of labor or cost of labor. January 2005.

NO OTHER WARRANTIES EXPRESS OR IMPLIED SHALL APPLY INCLUDING ANY WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE. CONPROCO CORP. SHALL NOT BE LIABLE UNDER ANY LEGAL THEORY FOR SPECIAL OR CONSEQUENTIAL DAMAGES.

conproco[®]
CORPORATION

17 PRODUCTION DRIVE, DOVER, NEW HAMPSHIRE 03820
TELEPHONE 800.258.3500 • FAX 603.743.5744 • WEB ADDRESS www.conproco.com